ICONIK 200Tex

Datasheet

Classification	Norm	Tarkett Value
Product type	EN ISO 26986	Expanded (cushioned) poly(vinyl chloride) floor covering
Domestic classification	EN ISO 10874	21 Moderate/Light
Binder content	ISO 11638	Type I
Technical Characteristics	**Norm**	**Tarkett Value**
Total thickness	ISO 24346	2 mm
Wear layer thickness	ISO 24340	0,15 mm
Total weight	ISO 23997	1300 g/m²
Performance for CE Marking	**Norm**	**Tarkett Value**
Declaration of Performance #	EN 14041	0007-0066-DOP-2022-11
Reaction to fire	EN 13501-1	Cfl-s1
Slip resistance (EN 13893)	EN 13893	Class DS (μ ≥ 0,30)
Slip resistance	DIN 51130	R10
Static Electrical Propensity	EN 1815	Antistatic (≤ 2 kV)
Thermal resistance	ISO 10456	0.02 m²•K/W
Technical Performance	**Norm**	**Tarkett Value**
Residual indentation	EN ISO 24343-1	≤ 0,35 mm
Impact sound reduction - ΔLw	EN ISO 717-2	15 dB
Light fastness	ISO 105-B02	≥ 6
Chemical resistance	ISO 26987	Not affected
Underfloor heating		Suitable (subfloor temperature maximum 27°C)
Dimensional stability	EN ISO 23999	≤ 0,15 %
Curl resultant to heat	ISO 23999	≤ |8| mm
Sustainability performances	**Norm**	**Tarkett Value**
Recyclability through ReStart®		Offcuts / Post-use - Contact Tarkett for more information
Recycled content		35 %
Carbon Footprint (Cradle-to-Gate, EPD Modules A1-A3)		3,63 kg CO_2eq /m²
Total Carbon Footprint (EPD Modules A-D, incl. recycling scenario)		2,41 kg CO_2eq /m²
Total VOC Emissions (after 28 days)	EN 16516	Gold (≤ 100 µg / m³)
BREEAM rating		A+
Formaldehyde emission		E1
Dimensions and designs		
Roll		Roll 2 x 25 m Roll 3 x 25 m Roll 4 x 25 m
Number of designs available		26

The above information is subject to modification for the benefit of further improvement (24/04/2026). According to the European Regulation N°305/2011 for CE Marking, the Declarations of Performance are available on our website https://www.tarkett.com. Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for the instructions.